

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
4 July 2002 (04.07.2002)

PCT

(10) International Publication Number  
**WO 02/051911 A1**

- (51) International Patent Classification<sup>7</sup>: C08G 75/08, G02B 1/04
- (21) International Application Number: PCT/EP01/15100
- (22) International Filing Date:  
20 December 2001 (20.12.2001)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:  
09/748,653 22 December 2000 (22.12.2000) US
- (71) Applicant (*for all designated States except US*): ES-SILOR INTERNATIONAL COMPAGNIE GENERALE D'OPTIQUE [FR/FR]; 147 rue de Paris, F-94227 Charenton Cedex (FR).
- (72) Inventors; and
- (75) Inventors/Applicants (*for US only*): JALLOULI, Aref Ben Ahmed [TN/US]; 13433 104th Avenue N., Largo, FL 33774 (US). OBORDO, Joey, Oliveros [US/US]; 13416 88th Avenue N, SEMINOLE, FL 33776 (US). TURSHANI, Yassin, Yusef [US/US]; 8073 Somerset Drive, LARGO, FL 33773 (US).
- (74) Agents: CATHERINE, Alain et al.; Cabinet Harle et Phe-  
lip, 7 Rue de Madrid, F-75008 Paris (FR).
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

**Published:**

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

*For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*



WO 02/051911 A1

(54) Title: DIEPISULFIDE BASED PREPOLYMERS AND THEIR USE IN THE OPTICAL FIELD

(57) Abstract: The room temperature polymerizable composition comprises at least one polymerizable monomer having at least one episulfide functionality and an effective amount of at least one (alkoxyphenyl)phosphine polymerization catalyst.

## DIEPISULFIDE BASED PREPOLYMERS AND THEIR USE IN THE OPTICAL FIELD

5

## (1) Field of the invention.

The present invention relates to stabilized, liquid diepisulfide based prepolymers, a method for preparing such prepolymers, a method for polymerizing curing the prepolymers into final polymer materials and their application for making transparent optical articles such as ophthalmic lenses.

10

## (2) Description of the prior art

Diepisulfide based resins are of major interest in the optical field owing to their high refractive indexes of 1.7 or more.

Document US-A-5.807.975 discloses thermal polymerization and curing of diepisulfides, in particular for the manufacture of optical materials such as a lens material for spectacles. This thermal polymerization/curing of diepisulfides lasts for several hours, generally about 20 hours.

15

Document EP-0.942.027 discloses an optical resin prepared by curing a polymerizable composition comprising a (thio)epoxy compound having at least one intramolecular disulfide bond. The curing catalysts which may be used are typically tertiary amines, phosphines, Lewis acids, radical polymerization catalysts and cationic polymerization catalysts. Lengthy polymerization time are reported.

20

Document WO 00/26272 discloses a process for making thio containing resins which comprises polymerizing a composition comprising at least one diepisulfide compound and as polymerization catalyst, an alkaline metal, alkaline-earth metal or ammonium salt of an acid having a pKa ranging from 0.5 to 14.

25

Although, such a polymerization process leads to fast polymerization / curing of the composition, the process is very difficult to control due to the highly exothermic polymerization reaction and often results in a charred resin inappropriate for making optical articles such as ophthalmic lenses.

5

## SUMMARY OF THE INVENTION

It has now been discovered that it is possible to safely prepare a liquid diepisulfide based prepolymer which is stable in time, the prepolymer being  
10 able to be later safely polymerized / cured into a transparent resin useful for making optical articles such as ophthalmic lenses.

Thus, an object of the present invention is a stabilized, liquid, diepisulfide based prepolymer useful for making transparent final resins.

It is another object of the present invention to provide a process for  
15 making a stabilized, liquid, diepisulfide based prepolymer.

It is a further object of the present invention to provide a process for making a transparent optical article through fast polymerization / curing of a stabilized, liquid, diepisulfide based prepolymer.

These and other objects are attained by providing a stabilized, liquid,  
20 diepisulfide base prepolymer having a viscosity at 25°C ranging from 20 to 33000 cPs, preferably from 100 to 1000 cPs.


By a "stabilized" prepolymer there is meant a prepolymer the viscosity of which does not vary and particularly does not increase more than 20% when stored at 20°C over a period of 7 days, preferably 10 days and more preferably  
25 one month.

By a "liquid" prepolymer there is meant a prepolymer which can be poured and cast into a casting mold such as a casting mold for making ophthalmic lenses.

## DETAILED DESCRIPTION OF THE INVENTION AND PREFERRED EMBODIMENTS


5 The stabilized, liquid, prepolymers of the invention are prepared by polymerizing a monomer composition comprising at least one diepisulfide monomer in the presence of an anionic initiator and a halogenated inhibitor.

Suitable diepisulfide monomers are diepisulfides of formula :



in which  $R^1$  and  $R^2$  are, independently from each other, H, alkyl, aryl, alkoxy, aryloxy, alkythio or arylthio ;  $R^3$  and  $R^4$ , independently from each other,

15



20 where  $R^a$  designates H, alkyl, aryl, alkoxy, aryloxy, alkythio or arylthio acid,  $n$  is an integer from 0 to 4 and  $m$  is an integer from 0 to 6.


$R^5$ ,  $R^6$ ,  $R^7$ ,  $R^8$  each represents an hydrogen atom or a hydrocarbon group having 1 to 10 carbon atoms, and preferably a methyl group.

Preferably, each  $R^5$ ,  $R^6$ ,  $R^7$ ,  $R^8$  represents a hydrogen atom.

The preferred diepisulfide monomers are those having at least one intramolecular disulfide bond.

A preferred class of diepisulfide monomers is comprised of diepisulfide monomers of formula :

5




in which  $\text{R}^1$ ,  $\text{R}^2$ ,  $\text{R}^3$  and  $\text{R}^4$  are defined as above.

In  $\text{R}^1$ ,  $\text{R}^2$ ,  $\text{R}^3$ ,  $\text{R}^4$  and  $\text{R}^a$ , the alkyl and alkoxy groups are preferably  $\text{C}_1$ - $\text{C}_6$ , more preferably  $\text{C}_1$ - $\text{C}_4$  alkyl and alkoxy groups such as methyl, ethyl, propyl, butyl, methoxy, ethoxy, propoxy and butoxy.

Specific examples of diepisulfide monomers are bis(2,3-epithiopropyl)disulfide, bis(2,3-epithiopropyldithio)methane, bis(2,3-epithiopropyldithio)ethane, bis(6,7-epithio-3,4-dithioheptane)sulfide, 1,4-dithian-2,5-bis(2,3-epithiopropyldithiomethyl), 1,3-bis(2,3-epithiopropyl-dithiomethyl)benzene, 1,6-bis(2,3-epithiopropyldithio)-2-(2,3-epithiopropyl-dithioethylthio)-4-thiahexane and 1,2,3-tris(2,3-epithiopropyldithio)propane.

The preferred diepisulfide monomer is bis(2,3-epithiopropyl)disulfide.

20



The monomer compositions may comprise solely as polymerizable monomer a diepisulfide monomer of formula (I) or a mixture of such diepisulfide monomers or it may also include other polymerizable monomers.

These additional monomers are compounds having two or more functional groups capable of reacting with an episulfide group or compounds having one or more of these functional groups and one or more of other homopolymerizable groups.


5 These additional monomers include epoxy compounds, polythiols, unsaturated ethylenic compounds such as vinyl ether or (meth)acrylate compounds, polyvalent carboxylic acids and anhydrides, thiocarboxylic acids, thio alcohols, thiophenols, polyphenols, amines and amides.

Preferred additional monomers are polythiol, epoxy compounds, acrylate  
10 and (meth)acrylate compounds, especially polythiol compounds.

Among the preferred epoxy compounds there may be cited the compounds of formulas :



15




where X is O or S, R<sup>b</sup> is H, alkyl or aryl and preferably alkyl or aryl, and R<sup>1</sup>, R<sup>2</sup>, R<sup>3</sup>, R<sup>4</sup>, m and n are defined as above.

20 Typical examples of the unsaturated ethylenic compounds include ethylene glycol dimethacrylate, propylene glycol dimethacrylate, tetramethylene glycol dimethacrylate, polyethylene glycol dimethacrylate, trimethylolpropane triacrylate, pentaerythritolpropane trimethacrylate,

ethoxylated bisphenol A diacrylate, 1,6-hexanediol dimethacrylate, urethane diacrylate, epoxy diacrylate, diallylphthalate, and divinyl benzene.



The polythiol monomer may be any suitable polythiol having two or more, preferably two to four, thiol functions.

5 The polythiol monomers can be represented by formula :




10 In which  $n'$  is an integer from 2 to 6 and preferably 2 to 4, and  $R'$  is an organic group of valency equal to  $n'$ .

Useful polythiol monomers are those disclosed in EP-A-394.495 and US-A-4.775.733 and the polythiols corresponding to the following formulas :




, and





Among the preferred polythiol monomers there may be cited aliphatic  
 5 polythiols such as pentaerythritol tetrakis mercaptopropionate, 1-  
 (1'-mercaptoethylthio)-2,3-dimercaptopropane, 1-(2'-mercaptopropylthio)-2,3-  
 dimercaptopropane, 1-(-3'-mercaptopropylthio)-2,3 dimercaptopropane,  
 1-(-4'-mercaptobutylthio)-2,3 dimercaptopropane, 1-(5' mercaptopentylthio)-  
 2,3 dimercaptopropane, 1-(6'-mercaptohexylthio)-2,3-dimercaptopropane, 1,2-  
 10 bis(-4'-mercaptobutylthio)-3-mercaptopropane, 1,2-bis(-5' mercaptopentyl-  
 thio)-3-mercaptopropane, 1,2-bis(-6'-mercaptohexyl)-3-mercaptopropane,  
 1,2,3-tris(mercaptomethylthio)propane, 1,2,3-tris(-3'-mercaptopropyl-  
 thio)propane, 1,2,3-tris(-2'-mercaptoethylthio)propane, 1,2,3-tris(-4'-mercapto-  
 butylthio)propane, 1,2,3-tris(-6'-mercaptohexylthio)propane, methanedithiol,  
 15 1,2-ethanedithiol, 1,1 propanedithiol, 1,2-propanedithiol, 1,3-propanedithiol,  
 2,2-propanedithiol, 1,6-hexanethiol-1,2,3-propanetrithiol, and 1,2-bis(-2'-  
 mercaptoethylthio)-3-mercaptopropane.

Among the preferred polythiols there may be cited polythiols of  
 formulas :

20







5

mixtures thereof.

Examples of polythiol compounds include 1,2,3-trimethylolpropane tri(thioglycolate), pentaerythritol tetra(thioglycolate), pentaerythritol tetra(3-  
 10 mercaptopropionate), 1,2,3-trimethylolpropane tri(3-mercaptopropionate), thioglycerol, dithioglycerol, trithioglycerol, dipentaerythritol hexa(2-mercantoacetate), and 3,4,5,6-tetrachloro-1,2-dimercapto benzene.


Among the (meth)acrylate compounds, there may be cited alkyl ( $\text{C}_1\text{-C}_6$ ) (meth)acrylate such as methyl(meth)acrylate, ethyl(meth)acrylate,  
 15 propyl(meth)acrylate and butyl(meth)acrylate.

The additional monomers usually represents 0 to 80% by weight preferably 0 to 50% by weight, of the total weight of polymerizable monomers present in the composition.

The composition may also include other optional ingredients classically  
 20 used in the formulation of polymerizable compositions such as mold release agents, antioxidants, dyes and UV light absorbers. These and other ingredients may be employed in their customary amounts for their customary purposes.

The polymerizable monomer composition of the invention includes at least one anionic polymerizable initiator.

Such anionic polymerization initiators are salts of formula :



5 wherein  $M^{p+}$  is a cation selected from the group consisting of alkaline metals, alkaline earth metals, transitions metals and ammonium groups of formula  $NR_4^+$  in which R is an alkyl radical,

$Y^-$  is an anion such as the corresponding acid YH has a pKa fulfilling the condition  $0.5 \leq pKa \leq 14$ ,

10 p is the valency of the cation, and

$n = m \cdot p$ .

The preferred metallic cation of the salts are  $Li^+$ ,  $Na^+$ ,  $K^+$ ,  $Rb^+$ ,  $Mg^{2+}$ ,  $Ca^{2+}$ ,  $Ba^{2+}$  and  $Al^{3+}$ . The particularly preferred metallic cations are  $Li^+$ ,  $Na^+$ , and  $K^+$  due to their absence of color and solubility in the composition.

15 Transition metals are less preferred because the salts thereof lead to coloured compositions and therefore coloured polymerized resins.

The preferred  $NR_4^+$  groups are those in which R is a  $C_1$ - $C_8$  alkyl radical and more preferably, a methyl, ethyl, propyl, butyl or hexyl radical.

The salts shall be used in the polymerizable composition in an effective  
20 amount, i.e. an amount sufficient to promote the thermal or room temperature polymerization of the composition.

Generally, the salt will be present in amounts ranging, based on the total weight of the polymerizable monomers, from 5 to 10000 parts per million (ppm), preferably 100 to 5000 ppm.

25 Preferably,  $Y^-$  is an anion such as the corresponding acid YH which fulfils the condition  $0.5 \leq pKa \leq 10$  and more preferably  $0.5 \leq pKa \leq 8$ .

Preferably, the anion  $Y^-$  is selected from the group consisting of thiocyanate, carboxylate, thiocarboxylate, acetylacetonate, diketone,

acetoacetic, ester, malonic, ester, cyanoacetic ester, ketonitrile and anion of formula  $RS^-$  wherein R is a substituted or non-substituted alkyl group or phenyl group.

Preferably, the alkyl group is a  $C_1$ - $C_6$  alkyl group, such as methyl, ethyl and propyl.

The preferred anions  $Y^-$  are  $SCN^-$ , acetylacetonate, acetate, thioacetate, formate and benzoate.

Examples of  $pK_a$  (acid/base) corresponding to the polymerization initiators are given in the table below :


ACID	ANION	Pka
HSCN	$SCN^-$	0.85
HCOOH	$HCOO^-$	3.8
$C_6H_5COOH$	$C_6H_5COO^-$	4.2
$CH_3COOH$	$CH_3COO^-$	4.8
$C_6H_5SH$	$C_6H_5S^-$	7.8
$CH_3COCH_2COCH_3$	$CH_3CO^-CHCOCH_3$	9

Preferred polymerization initiators are KSCN and MeCOOK.

The polymerization initiator preferably also further includes at least one electro-donor compound.

The electro-donor compound is preferably a crown-ether.

The preferred crown-ethers may be represented by formula :



where  $R^9$  and  $R^{10}$  are polymethylene groups, preferably methylene or ethylene groups, and  $x$  is an integer from 3 to 6.

Preferred crown-ether is 1,4,7,10,13, 16-hexaoxacycloctadecane (18-crown-6).

5 The electro-donor compounds are present, based on total weight of the polymerizable monomers present in the composition in amounts ranging from 0 to 6%, preferably from 0.03 to 3% by weight.

Generally, the molar ratio  $\frac{[\text{electrodonor}]}{[\text{initiator}]}$  ranges from 1 to 10.

10 The polymerization initiator is preferably introduced in the polymerizable composition as a solution in a solvent.

Appropriate solvents are alcohols, such as alcanols and mercaptoalcanols, ketones such as acetone, acetonitrile, dimethylsulfoxide and tetrahydrofuran. Preferred solvent is 2-mercaptoethanol.

15 The polymerizable composition also contains at least one halogenated polymerization inhibitor.

By polymerization inhibitor, it is meant a compound which decreases the rate of polymerization of a given polymerizable composition when compared to a similar polymerizable composition free of such polymerization inhibitor.

20 The halogenated inhibitor may be a chlorinated, a brominated, a iodinated or a mixed halogenated compound.

The halogenated inhibitor may be represented by the following formula :






25 In which  $R$  is a carbon atom, or a hydrocarbon group such as an alkyl radical or an aromatic radical,  $A$  is a halogen or a halogeno alkyl radical and  $y$  is an integer from 1 to 4, preferably from 1 to 2.


The preferred halogenated inhibitors may be represented by formula :



where  $A_1$  is an aryl radical eventually substituted, such as a phenyl,  
 5 naphthyl, anthryl or biphenyl radical, X is a halogen atom such as I, Br or Cl, and  
 z is a integer from 1 to 4, preferably 1 to 2.


Among the preferred halogenated inhibitors there may be cited :





The most preferred halogenated inhibitor is :

5



10 The amount of halogenated inhibitor used may vary depending upon the monomers and the initiators used to formulate the polymerizable composition as well as the desired rate of polymerization. However, the amount of halogenated inhibitor shall be sufficient to avoid charring of the polymerizable composition.

Usually, the amount of inhibitor present in the polymerization composition expressed as the molar ratio of halogenated inhibitor to the polymerization initiator (with the exclusion of the electro-donor compound) 15 will range from 0.1 to 350, preferably from 1 to 50, and more preferably from 1 to 10.

The monomer compositions may also include a variety of adjuvants such as photostabilizers, UV absorbents, antioxidants, anti-coloring agents, dyes, 20 fillers and internal mold release agents in the usual proportions.

The prepolymer synthesis, i.e. polymerization of the monomer composition can be carried out in bulk, in solution, in suspension or in emulsion.

Polymerization of the monomer compositions is preferably carried out in bulk at room temperature, by simply adding together the different ingredients of the compositions under stirring, then letting the polymerization proceed with or without stirring. Preferably the halogenated inhibitor is added to the monomer prior to the addition of the polymerization initiator.

As previously mentioned the prepolymers of the invention have a viscosity at 25°C ranging from 20 to 33000 centipoises, preferably 100 to 1000 centipoises.

All viscosity measurements are made with the same viscosimeter (Brookfield LVDVI) and following the same protocole but using S18 spindle for monomers and prepolymers of low viscosity (20 to 1000 cPs) and S31 spindle for prepolymers of higher viscosity ( $\geq 5000$  and up to 50000 cPs).

Selection of spindle speed is made as follows :

For any given spindle/speed combination, the maximum range is equal to the spindle factor multiplied by 100 and the minimum range equals the factor multiplied by 10.

For the S-18 spindle, sample size is 8.0 ml and spindle factor is  $30/N$  where N is the spindle speed (rpms) and for S-31 spindle, sample size is 10.0 ml and the spindle factor  $300/N$ .

Thus, using S-18 spindle at 2.5 rpms the spindle factor will be  $30/2.5 = 12$  and the viscosity range 120 cPs to 1200 cPs.

Range efficiency (%) corresponds to the ratio of the measured viscosity for the sample divided by the maximum range and multiplied by 100. The higher the range efficiency, the more accurate is the viscosity measurement. Acceptable range efficiency is 10% to 99.9%.

Optimization of spindle speed may be effected as follows :

Assuming that at a spindle speed of 1.5 rpms the range efficiency is only 33.8%, doubling the spindle speed to 3.0 rpms would give a range efficiency of

67.6%. Further increasing the spindle speed from 3.0 to 4.0 rpms would give a 25% increase of the range efficiency to 84.5%. But an increase of spindle speed from 4.0 to 5.0 rpms would give a 20% increase of the range efficiency to 101.4% which is an error (reading exceeds the 100% limit). Therefore, the  
5 viscosity measurements will be taken at a speed of 4 rpms with approximately a 84.5% range efficiency.

All viscosity measurements are made at 25°C.

All refractive index measurements are made at 25°C using sodium D line  
589 nm.

10 The prepolymers of the invention can be safely cured into a transparent resin, in bulk polymerization.

Curing may be effected by simply heating the prepolymer or a mixture of the prepolymers at a temperature up to 80°C, preferably ranging from 40 to 80°C.

15 Curing can be conducted at room temperature by incorporating an additional amount of the polymerization initiator or another initiator to the prepolymer or mixture of prepolymers.. The amount of additional or other polymerization initiator may vary depending upon the desired rate of curing but must be such that charring is avoided. This amount usually ranges from 100 to  
20 2000 ppm.

Alternatively, initial raw monomers such as diepisulfides and/or polythiols as well as an additional amount of the polymerization initiator or another initiator can be added to the prepolymer or mixture of prepolymers, and the resulting composition can be cured at room temperature.

25 The amount of raw monomers that is usually added will range from 5 to 95%.

The additional amounts of polymerization initiator as previously indicated may be widely varied, but usually will range from 100 to 2000 ppm.



Curing time up to the obtention of a gel usually ranges from 5 to 30 minutes.

Curing may be effected in a mold, such as a two parts mineral glass mold for obtaining an optical article such as an ophthalmic lens.

5 Whenever necessary, a mixing apparatus may be used for either the mixing step of the monomer components of the monomer composition leading to the prepolymer of the invention or the mixing steps of raw monomers or additives with the prepolymer of the invention.

Static mixers, small reactors with magnetic bar, mechanical mixers, 10 screw mixers or ultrasonic mixing system may be used.

A screw mixer is preferably used.

In a preferred embodiment, the components to be mixed are added inside a small reactor chamber and then mixed with a screw mixer.

The following examples illustrate the present invention. In these 15 examples, unless otherwise stated, all parts and percentage are by weight.

#### Examples 1 to 13 and comparative example C1


These examples illustrate the preparation of the prepolymers of the invention.

Several prepolymers were prepared by bulk polymerizing bis(2,3- 20 epithiopropyl)disulfide using mixtures of MeCOOK and 18.crown.6 as the polymerization initiator in the presence of various amounts of benzylchloride as the inhibitor and eventually with various amounts of polythiols.

The polymerization initiator was added in the form of a solution in 2-mercaptoethanol.

25 Addition of the different ingredients and polymerization were made at room temperature. Magnetic stirring was used during the additions and stopped once the last ingredient added.

All polymerizations were done using 10g samples of bis(2,3-epithiopropyl)disulfide.



Compositions and results are given in Table I :

5

TABLE I


Run N°	Polythiol A (% by weight)	MeCOOK (ppm)	Molar ratio BzCl/MeCOOK	Results Time
1	-	52	0.142	Clear liquid after 6 days
2	-	43	0.331	Clear liquid after 6 days
3	-	61	0.422	Clear liquid after 6 days
4	-	51	1.004	Clear liquid after 6 days
5	-	49	1.572	Clear liquid after 6 days
6	-	54	1.904	Clear liquid after 10 days
7	-	58	3.543	Clear liquid after 10 days
8	-	34	12.762	Clear liquid after 10 days
9	-	313	37.532	Clear liquid after 31 days
10	-	287	347.300	Clear liquid after 31 days
11	10.53	308	2.039	Slightly yellow viscous liquid after 37 days
12	10.18	300	5.324	Slightly viscous liquid After 5 days
13	10.98	321	8.843	Cloudy liquid after 37 days
C1	-	304	0	Char after 50-86 min.

In runs 1 to 8 there was used 0.05-0.09% by weight of 2-mercaptoethanol  
 10 (as solvent) and the molar ratio of 18-crown-6 to MeCOOK was 2.256.


In runs 9 to 13 and C1 there was used 0.5 to 0.6% by weight of 2-mercapto ethanol and the molar ratio of 18-crown-6 to the MeCOOK was 2.4.

In all runs there were added 0.4-0.5 ppm of Blue dye.


Polythiol A is a mixture of the following three polythiols in the  
5 respective weight percent amounts (molar amounts).



10



15



Such polythiol A is described in US patent N°5.837.797 (example 1).

Blue dye : 1,4-[(2,6-dibromo-4-methylphenyl)amino]-1,4-  
20 anthracenedione (also known as Morplas Violet 3B)

BzCl : Benzyl chloride

The liquid prepolymers made are perfectly miscible with the starting raw monomers.

Examples 14 and 15 and comparative example C'1

25 Prepolymers were prepared by bulk polymerizing bis(2,3-epithiopropyl)disulfide and polythiol A using a mixture of MeCOOK and 18-

crown-6 as initiator and  $\text{CCl}_4$  as inhibitor in the presence of 2-ethylhexanoic acid.

The initiator was added in the form of a solution in 2-mercaptoethanol.

Compositions, polymerization conditions and results are given in Table

5 II.

Polymerizations were done using 10g samples of bis(2,3-epithiopropyl)disulfide.

TABLE II

Run N°	Molar ratio 2-ethylhexanoic/ MeCOOK	Polythiol A (%)	$\text{CCl}_4$ (%)	T(°C)	Stirred	Result	Time
14	1.062	10.39	1.91	RT	No	Liquid	42 days
15	1.028	10.18	1.92	40°C	No	Liquid	42 days
Comparative C'1	1.152	10.41	0	RT	No	Gel	1-16 hours

10

The amount of MeCOOK was 295-325 ppm, the molar ratio 18-crown-6/Me COOK was 2.4 and the amount of 2-mercapto ethanol was 0.5-0.6%.

RT = Room temperature (20°C).

Examples 16 to 26

15 Eleven prepolymers were prepared by polymerizing bis(2,3-epithiopropyl)disulfide using mixtures of MeCOOK and 18-crown-6 as initiator in the presence of different amounts of benzyl chloride as the inhibitor.

The polymerization initiator was added as a solution in 2-mercaptoethanol.

20

Addition of the different ingredients was made at room temperature under stirring. Polymerization was made at room temperature without stirring.

All polymerizations were done using 100g samples of bis(2,3-epithiopropyl)disulfide.

Viscosities of the prepolymers were measured as previously described.

Compositions and results are given in Table III.

TABLE III

Run N°	Polythiol A (% by weight)	MeCOOK (ppm)	Molar ratio BzCl/MeCOOK	Viscosity (cPs)		
				245 (1 day)	298 (4 days)	299 (7 days)
16	-	300	2.100	245 (1 day)	298 (4 days)	299 (7 days)
17	-	302	4.091	59 (1 day)	73 (4 days)	74 (7 days)
18	-	300	6.264	35 (1 day)	44 (4 days)	44 (7 days)
19	5.057	303	2.127	91 (1 day)	167 (4 days)	175 (7 days)
20	5.052	301	4.079	37 (1 day)	49 (4 days)	51 (7 days)
21	5.052	302	5.815	35 (1 day)	40 (4 days)	41 (7 days)
22	10.009	301	2.099	253 (1 day)	323 (5 days)	320 (8 days)
23	10.020	301	4.059	47 (1 day)	53 (5 days)	54 (8 days)
24	10.036	301	6.066	37 (1 day)	39 (5 days)	40 (8 days)
25	-	51	0.526	51 (3 days)	49 (6 days)	49 (10 days)
26	-	48	0.139	60 (1 day)	64 (3 days)	67 (7 days)

5 In runs 16-24, there were used 0.5% by weight of 2-mercaptoethanol and 0.5 ppm of Blue dye. The molar ratio of 18-crown-6 to MeCOOK was 2.4. There was no stirring during the polymerization.

In runs 25 and 26 there were used 0.1% by weight of 2-mercaptoethanol and 0.5 ppm of Blue dye. Molar ratio of BzCl to Me COOK was 2.3 and the  
10 mixture was stirred during the polymerization.

The results show that the viscosity of the prepolymer increases with time to stabilize within 4 days. The final viscosity decreases with increasing amounts of inhibitor.

#### Examples 27 to 29

15 These examples illustrate the influence of the stirring and of the polymerization temperature on the resulting prepolymers.

Three prepolymers were prepared by polymerizing bis(2,3-epithiopropyl)disulfide using mixtures of MeCOOK and 18-crown-6 as initiator in the presence of different amount of benzylchloride as the inhibitor.

The polymerization initiator was added as a solution in 2-mercaptoethanol.

Polymerization was effected either at room temperature or above with or without stirring.

5 All polymerizations were done using 100g samples of bis(2,3-epithiopropyl)disulfide.

Viscosities of the prepolymers were measured as previously described.

Compositions and results are given in table (IV).

10

TABLE IV

Run N°	MeCOOK (ppm)	Molar ratio 18-crown-6 / MeCOOK	Molar ratio BzCl/MeCOOK	2-mercapto- ethanol (%)	Stirring	T(°C)	Viscosity		
							260 (1day)	281 (2 days)	282 (7 days)
27	309	2.205	2.124	0.5	Yes	20	245 (1 day)	248 (4 days)	299 (7 days)
28	300	2.400	2.100	0.5	No	20	1152 (1 day)	1291 (2 days)	1830 (7 days)
29	308-309	2.205	2.058	0.5	Yes	40			

15 These examples show that stirring increases the rate of obtention of a stable prepolymer. Increasing the temperature increases the viscosity which keeps increasing with time without reaching a stable value.

#### Examples 30 to 34

These examples show the influence of the order of addition of the different reactants.

20 Several runs were carried out on 100g batches of bis(2,3-epithiopropyl)disulfides using different orders of addition of the reactants. Compositions, order of addition of the reactants and results are given in Table V.

The results show that the reaction is best controlled when benzyl chloride is first added to the monomer, followed by the initiator (run 34). The mixing upon addition is also important. It is worth noticing the lower reactivity of the system where the initiator solution was first mixed with benzyl chloride prior to addition to the monomer (run 33). The differences in the final viscosity of runs 32, 31 and 33 are probably due to differences in the amounts of benzyl chloride used rather than differences in the order of addition of the reactants.



TABLE V

Run N°	BzCl	Order of addition	Tmax (°C)	Viscosity (cPs)
30	3.001	1) 0.6215 BDS 2) 58.7193 g M 3) 0.1210 g BzCl 4) 0.6999 g initiator 5) 40.66 g M (S)	<u>49.7@15 min</u>	<u>2541@116 hrs</u>
31	3.338	1) 0.3117 g BDS 2) 2.3932 g M (S) 3) 10.0004 g M (S) 4) 0.6861 g initiator 5) 0.1319 BzCl 6) 87.89 g M (S)	<u>31.7@40 min</u>	<u>516@92 hrs</u> <u>566@140 hrs</u>
32	3.243	1) 0.3104 g BDS 2) 12.3970 g M (S) 3) 0.1271 g BzCl (S) 4) 0.6805 g M (S) 5) 87.98 g M (S)	<u>31.5@40 min</u>	<u>521@20 hrs</u> <u>578@48hrs</u>
33	3.571	1) 0.3175 g BDS 2) 12.3946 g M (S) 3) [0.6831 g initiator + 0.1405 g BzCl(S)] (S) 4) 88.00 g M (S)	<u>≈ 26@30 min</u>	<u>237@20 hrs</u> <u>263@48 hrs</u>
34	3.756	1) 0.3077 g BDS 2) 100.42 g M (S) 3) 0.1486 g BzCl (S) 4) 0.6869 g MeCOOK (S)	<u>35.5@45 min</u>	<u>203@1.87 hrs</u> <u>418@28 hrs</u>

BDS : solution made from 0.0037 g Blue Dye + 22.9947 g bis(2,3-epithiopropyl)disulfide

Initiator : solution made from 0.3914 g MeCOOK + 2.3557 g (18,6) crown + 6.0181 g 2-

5 mercaptoethanol

S : Stirred

M : bis(2,3-epithiopropyl)disulfide.

Examples 35 to 38

Four prepolymers were synthesized at room temperature using 100g batches of bis(2,3-epithiopropyl)disulfide monomer and different amounts of benzyl chloride. They were characterized by their viscosity and refractive index.

5 Compositions and results are given in Table VI :

TABLE VI

Run <sup>a)</sup> N°	BzCl/MeCOOK	Viscosity (cPs) @ 4 days	Viscosity (cPs) @ 19 days	n <sub>D</sub> @ 4 days	n <sub>D</sub> @ 19 days
36	2.224	29400 <sup>b)</sup>	28020 <sup>c)</sup>	1.6866 <sup>b)</sup>	1.6865 <sup>c)</sup>
37	4.191	257	257	1.6656	1.6658
38	6.400	101	102	1.6587	1.6590
39	8.160	74	71	1.6559	1.6562

a) All runs contained : [MeCOOK]≈305 ppm, [(18,6)]≈1832 ppm, [2-mercaptoethanol]≈0.47%

b) At 5 days

10 c) At 18 days

The refractive index of the prepolymers at 25°C decreases when the ratio BzCl/MeCOOK used increases. The values of refractive index are about the same between 4 and 19 days, which indicates that the prepolymers made are  
15 stable.

The viscosity of the prepolymers at 25°C decreases when the ratio BzCl/MeCOOK used increases. The values of viscosity are about the same between 4 and 19 days, which indicates that the prepolymers made are stable.

Examples 39 to 47

20 A series of nine chlorinated aromatics was evaluated as inhibitors, including benzyl chloride. All of them gave stable and clear prepolymers, except  $\alpha$ ,  $\alpha$  dichlorotoluene that gave a char.

In all runs, there were used 300 ppm MeCOOK, 1800 ppm of 18-crown-6 and 0.45% of 2-mercaptoethanol.

Different amounts of inhibitors were used as indicated by the molar ratios inhibitor/MeCOOK of Table VII. Results are also given in Table VII.

TABLE VII

Run N°	Inhibitor	Molar ratio Inhibitor/MeCOOK	Experimental Refractive index @ 7 days	Calculated viscosity (cPs)
39	Benzyl chloride	2.019	1.6868	30070
		4.153	1.6659	285
		7.634	1.6567	76
40	1,2-bis(chloromethyl) benzene	2.934	1.6546	59
		4.037	1.6522	44
		8.891	1.6478	28
41	1,3-bis(chloromethyl) benzene	2.134	1.6760	1928
		4.616	1.6588	99
		7.756	1.6528	48
42	1,4-bis(chloromethyl) benzene	1.829	1.6708	673
		3.648	1.5607	129
		8.539	1.6516	42
43	4,4- bis(chloromethyl)1,1- biphenyl	2.122	1.6676	378
		4.506	1.6559	68
		7.503	1.6474	27
44	2-chloromethyl phenyl isocyanate	1.836	1.6450	22
		4.030	1.6446	21
		8.742	1.6447	21
45	4-chloromethyl phenyl isocyanate	2.363	1.6472	27
		4.368	1.6454	22
		7.383	1.6453	22
46	1-chloromethyl 2,4- diisocyanatobenzene	2.821	1.6447	21
		4.512	1.6449	21
		7.688	1.6454	22
47	$\alpha, \alpha$ dichlorotoluene	3.052	-	-
		3.272	-	-
		8.537	-	-

Calculated viscosities were determined using the graph of figure 1 which is a graph of  $\ln(\text{viscosity})$  as a function of the refractive index.

#### Examples 48 to 51

These examples illustrate the use of the prepolymers of the invention for making cured transparent resins.

Samples of 10 g were prepared and placed in glass vials by adding to a prepolymer of the invention various amounts of polythiol A and MeCOOK. The prepolymers used contain 99.24% by weight bis(2,3-epithiopropyl)disulfide, 308 ppm MeCOOK, 1827 ppm 18-crown-6, 0.47% by weight 2-mercaptoethanol, 820 ppm of benzyl chloride and 0.5 ppm of Blue dye.

The mixture was stirred magnetically for about 10 s, then kept at room temperature with no stirring.

The amounts of reactants and the results are given in Table VIII.

TABLE VIII

Run N°	Prepolymer (%)	Polythiol A (%)	Added [MeCOOK] (ppm)	Result	Gel Time
48	88.7	10.4	77	Gel	> 24 hrs
49	88.3	10.3	307	Gel	< 24 hrs
50	88.2	10.2	355	Gel	< 24 hrs
51	88.0	10.4	405	Yellow gel	8 min

#### Examples 52 to 54

A mixture was prepared using the same prepolymer as in examples 47 to 50 and adding to this polymer, polythiol A and MeCOOK. The amounts of the reactants are indicated in Table IX.

This mixture was used to form 2 mm thick flat lenses having a diameter of 85 mm using a classical two parts mineral glass mold.

The lenses were cured 1 hour at 80°C. The resulting lenses are perfectly clear.

TABLE IX


Run N°	Prepolymer (%)	Polythiol A (%)	Added [MeCOOK] (ppm)	Gel Time (min)
52	88.7	9.7	413	60
53	88.4	9.6	537	40
54	87.6	9.7	871	11

CLAIMS


1. A stabilized, liquid, diepisulfide based prepolymer having a viscosity  
 5 at 25°C ranging from 20 to 33000 centipoises.

2. The prepolymer of claim 1, wherein the viscosity at 25°C ranges from  
 100 to 1000 centipoises.

3. The prepolymer of claim 1 resulting from the polymerization in the  
 presence of an anionic polymerization initiator and a halogenated  
 10 polymerization inhibitor of a monomer composition comprising at least one  
 diepisulfide monomer of formula :



15 in which  $R^1$  and  $R^2$  are, independently from each other, H, alkyl, aryl,  
 alkoxy, aryloxy, alkythio or arylthio ;  $R^3$  and  $R^4$ , independently from each other  
 represent :




20

where  $R^a$  designates H, alkyl, aryl, alkoxy, aryloxy, alkythio or arylthio  
 acid, n is an integer from 0 to 4 and m is an integer from 0 to 6 and  $R^5, R^6, R^7,$

$R^8$  each represents a hydrogen atom or a hydrocarbon group having 1 to 10 carbon atoms.

4. The prepolymer of claim 3, wherein said at least one diepisulfide is a diepisulfide of formula :

5




in which  $R^1$ ,  $R^2$ ,  $R^3$  are as defined in claim 3.

5. The prepolymer of claim 3, wherein said at least one diepisulfide is selected from bis(2,3-epithiopropyl)disulfide, bis(2,3-epithiopropyl-dithio)methane, bis(2,3-epithiopropyldithio)ethane, bis(6,7-epithio-3,4-dithioheptane)sulfide, 1,4-dithan-2,5-bis(2,3-epithiopropyldithiomethyl), 1,3-bis(2,3-epithiopropyl-dithiomethyl)benzene, 1,6-bis(2,3-epithiopropyldithio)-2-(2,3-epithiopropyl-dithioethylthio)-4-thiahexane and 1,2,3-tris(2,3-epithiopropyldithio)propane.

6. The prepolymer of claim 3, wherein said at least one diepisulfide is bis(2,3-epithiopropyl)disulfide.

7. The prepolymer of claim 3, wherein the monomer composition further comprises at least one polythiol.

8. The prepolymer of claim 7, wherein said at least one polythiol is represented by formula :




25



In which  $n'$  is an integer from 2 to 6 and preferably 2 to 4, and  $R'$  is an organic group of valency equal to  $n'$ .



9. The prepolymer of claim 8, wherein said at least one polythiol is selected from polythiols of formulas :



5




10

mixtures thereof.

10. The prepolymer of claim 3, wherein the anionic polymerization initiator comprises a salt of formula :

15



wherein  $\text{M}^{\text{P}+}$  is a cation selected from the group consisting of alkaline metals, alkaline earth metals, transitions metals and ammonium groups of  
20 formula  $\text{NR}_4^+$  in which R is an alkyl radical,


$Y^-$  is an anion such as the corresponding acid  $YH$  has a  $pK_a$  fulfilling the condition  $0.5 \leq pK_a \leq 14$ ,

$p$  is the valency of the cation, and

$n = mxp$ .


5 11. The prepolymer of claim 10, wherein the anionic polymerization initiator is  $MeCOOK$  or  $KSCN$ .


12. The prepolymer of claim 3, wherein the halogenated polymerization inhibitor comprises a compound of formula :



where  $A_1$  is an aryl radical eventually substituted,  $X$  is a halogen atom and  $z$  is an integer of 1 to 4.

15 13. The prepolymer of claim 3, wherein the halogenated polymerization inhibitor is selected from :






5            14. The prepolymer of claim 13, wherein the halogenated polymerization inhibitor is benzyl chloride.

15. A process for making a stabilized, liquid, diepisulfide based prepolymer having a viscosity at 25°C ranging from 20 to 33000 centipoises which comprises polymerizing at room temperature a monomer composition  
 10   comprising at least one diepisulfide monomer in the presence of at least one anionic polymerization initiator and at least one halogenated polymerization inhibitor.

16. The process of claim 15, wherein the halogenated polymerization inhibitor is added to the monomer composition prior to the addition of the  
 15   anionic polymerization inhibitor.

17. The process of claim 15, wherein said at least one diepisulfide is a diepisulfide of formula :




in which  $R^1$ ,  $R^2$ ,  $R^3$  are as defined in claim 3.

18. The process of claim 15, wherein said at least one diepisulfide is selected from bis(2,3-epithiopropyl)disulfide, bis(2,3-epithiopropyl-dithio)methane, bis(2,3-epithiopropyldithio)ethane, bis(6,7-epithio-3,4-dithioheptane)sulfide, 1,4-dithian-2,5-bis(2,3-epithiopropyldithiomethyl), 1,3-bis(2,3-epithiopropyl-dithiomethyl)benzene, 1,6-bis(2,3-epithiopropyldithio)-2-(2,3-epithiopropyl-dithioethylthio)-4-thiahexane and 1,2,3-tris(2,3-epithiopropyldithio)propane.

19. The process of claim 15, wherein said at least one diepisulfide is bis(2,3-epithiopropyl)disulfide.


20. The process of claim 15, wherein the monomer composition further comprises at least one polythiol.



21. The process of claim 15, wherein said at least one polythiol is represented by formula :



In which  $n'$  is an integer from 2 to 6 and preferably 2 to 4, and  $R'$  is an organic group of valency equal to  $n'$ .

22. The process of claim 15, wherein said at least one polythiol is selected from polythiols of formulas :






5

mixtures thereof.

23. The process of claim 15, wherein the anionic polymerization initiator comprises a salt of formula :

10



wherein  $\text{M}^{\text{p}+}$  is a cation selected from the group consisting of alkaline metals, alkaline earth metals, transitions metals and ammonium groups of formula  $\text{NR}_4^+$  in which R is an alkyl radical,

15

$\text{Y}^-$  is an anion such as the corresponding acid YH has a pKa fulfilling the condition  $0.5 \leq \text{pKa} \leq 14$ ,

p is the valency of the cation, and

$n = \text{m} \times \text{p}$ .

20

24. The process of claim 15, wherein the anionic polymerization initiator is MeCOOK or KSCN.

25. The process of claim 23, wherein the anionic polymerization initiator further comprises a crown-ether.

26. The process of claim 25, wherein the crown-ether is 18-crown-6.

27. The process of claim 15, wherein the halogenated polymerization inhibitor comprises a compound of formula :






5


where  $A_1$  is an aryl radical eventually substituted, X is a halogen atom and z is an integer of 1 to 4.

28. The process of claim 15, wherein the halogenated polymerization inhibitor is selected from :

10



15



and  $CCl_4$  .

29. The process of claim 15, wherein the halogenated polymerization inhibitor is benzyl chloride.

30. The process of claim 15, wherein the amount of anionic polymerization initiator present ranges from 5 to 10000 ppm based on the total weight of polymerizable monomers.

31. The process of claim 15, wherein the molar ratio of the halogenated inhibitor to the polymerization initiator ranges from 0.1 to 350.

32. A process for making a cured, transparent, diepisulfide based resin which comprises :

- obtaining a stabilized, liquid, diepisulfide based prepolymer having a viscosity at 25°C ranging from 20 to 33000 centipoises ;
- adding to the prepolymer an effective amount of an anionic polymerization initiator ; and
- bulk polymerizing the prepolymer at least up to the obtention of a gel.

33. The process of claim 32, wherein bulk polymerization is carried out at room temperature.

34. The process of claim 33, wherein bulk polymerization up to the obtention of a gel lasts for 5 to 30 minutes.

35. The process of claim 32 which further comprises adding diepisulfide monomer and/or polythiol monomer prior to the bulk polymerization.

36. The process of claim 35, wherein bulk polymerization is carried out at room temperature.

37. The process of claim 36, wherein bulk polymerization up to the obtention of a gel lasts for 5 to 30 minutes.

38. The process of claim 32, wherein bulk polymerization is carried out in a lens casting mold.

39. The process of claim 35, wherein bulk polymerization is carried out in a lens casting mold.

40. Ophthalmic lens obtained by the process of claim 38.

41. Ophthalmic lens obtained by the process of claim 39.

42. A process for making a cured, transparent, diepisulfide based resin which comprises :

- 5       - obtaining a stabilized, liquid, diepisulfide based prepolymer having a viscosity at 25°C ranging from 20 to 33000 centipoises ;
- adding to the prepolymer an effective amount of an anionic polymerization initiator ;
- bulk polymerizing the prepolymer with heating at least up to the obtention of a gel.



1/1




FIG. 1

# INTERNATIONAL SEARCH REPORT

International Application No.  
P... EP 01/15100

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 7 C08G75/08 G02B1/04

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
IPC 7 C08G 602B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 1 006 374 A (MITSUBISHI GAS CHEMICAL CO) 7 June 2000 (2000-06-07) tables 1,2 example 5	1,40,41
X	EP 0 942 027 A (MITSUI CHEMICALS INC) 15 September 1999 (1999-09-15) cited in the application table 1	1,40,412
X	WO 00 26272 A (ESSILOR INT ;MCCLIMANS PAMELA ANNE (US); KEITA GABRIEL (US); WEBER) 11 May 2000 (2000-05-11) cited in the application claim 1; table 1	1,40,41
-/-		

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents :

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

\*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

\*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

\*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

\*G\* document member of the same patent family

Date of the actual completion of the international search

18 April 2002

Date of mailing of the international search report

07/05/2002

Name and mailing address of the ISA  
European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax (+31-70) 340-3016

Authorized officer

O'Sullivan, T

## INTERNATIONAL SEARCH REPORT

International Application No  
PCT/EP 01/15100

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	DE 15 70 447 A (DUNLOP RUBBER CO.) 18 September 1969 (1969-09-18) claim 1; example 1 table 4	1-42
A	US 3 582 521 A (VILLA JOSE L) 1 June 1971 (1971-06-01) claim 1 examples 1-7	1-42
A	US 3 679 616 A (VILLA JOSE L) 25 July 1972 (1972-07-25) claim 1; example 1	1-42

## INTERNATIONAL SEARCH REPORT

In International Application No

PCT/EP 01/15100

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 1006374	A	07-06-2000	EP 1006374 A2	07-06-2000
			JP 2000226451 A	15-08-2000
			JP 2000239384 A	05-09-2000
EP 0942027	A	15-09-1999	JP 2000230050 A	22-08-2000
			EP 0942027 A2	15-09-1999
			JP 11322930 A	26-11-1999
			US 6204311 B1	20-03-2001
			US 2001002413 A1	31-05-2001
			US 2002019511 A1	14-02-2002
WO 0026272	A	11-05-2000	US 5973098 A	26-10-1999
			AU 6203899 A	22-05-2000
			CN 1325414 T	05-12-2001
			WO 0026272 A1	11-05-2000
			EP 1124873 A1	22-08-2001
DE 1570447	A	18-09-1969	GB 1105603 A	06-03-1968
			DE 1570447 A1	18-09-1969
			FR 1435307 A	15-04-1966
			US 3515704 A	02-06-1970
US 3582521	A	01-06-1971	US 3725337 A	03-04-1973
			US 3767672 A	23-10-1973
JS 3679616	A	25-07-1972	NONE	

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**